

EU.P.S. Forest

General description: coloured asphalt shingle

bituminous compound	-		APP modified bitumen	
length	EN 544	mm	1000	+/-3
width	EN 544	mm	340	media
thickness	-	mm	3	+/-10%
exposed area	-	mm	145	-
adhesion system			self adhesive tabs	

Physical-chemical properties

weight	-	kg/m ²	9.8	+/-8%
mass of the fibreglass mat	-	g/m ²	100	+/-10%
bitumen single layer	EN 544	g/m ²	>1400	-
granules single layer	EN 544	g/m ²	>1300	-
mechanical resistance MD/CMD	EN 544	N/5 cm	>750/>450	-
nail resistance	EN 544	N	>100	-
granules adhesion	EN 544	-g	<1,5	-

Fire behaviour

classification according	EN 13501-5	B roof (t1)
classification according	EN 13501-1	E

Wrapping

type	polyethylene
shingles for bundle	24
m ² /bundle	3,5
m ² /pallet	180

TeMa North America llc
395 Steeley Way - Kearneysville WV 25430 U.S.A.
Phone (304) 724 0200
e-mail: info@temanorthamerica.com
www.temanorthamerica.com



Rev. 0 - 30/05/19